

04-10

**ROGERS WATER UTILITIES
ROGERS, ARKANSAS**

**SPECIFICATIONS FOR
ASPHALT CONCRETE COLD PLANT MIX MATERIAL
(TEMPORARY PAVEMENT REPAIR)
AUGUST 2007**

1. **SCOPE**

This specification governs the asphalt concrete cold plant mix material used for the temporary pavement repair of streets, parking lots and driveways from the results of utility cuts.

2. **COMPOSITION REQUIREMENTS**

a. The mixture shall conform to the requirements shown below.

<u>Sieve Size</u>	<u>Maximum Mix Percent by Wt. Passing</u>	<u>Tolerance (%)</u>
1/2"	100	
No. 4	60-80	± 7
No. 8	43-63	± 5
No. 50	15-28	± 4
No. 200	4-10	± 2
Asphalt Binder Content	3.5%-6.5%	± 0.4
Mineral Filler	3.0%	Minimum

3. **MATERIALS REQUIREMENTS**

The asphalt shall be an MC-250, MC-800, MC-3000 or a summer or winter grade seasonal type asphalt. The asphalt concrete cold plant mix material type asphalt shall comply with the AHTD Standard Specification for Highway Construction, Section 411-Asphalt Concrete Cold Plant Mix.